

LIDDING FILMS



TECHNICAL SUPPORT

We pride ourselves in providing high quality services and technical support to all customers.

CONTACT INFORMATION

For more information on any of our products or services, please contact us at:

Golden Eagle Extrusions, Inc.
1762 State Route 131
Milford, Ohio 45150
P - 800.634.3355
F - 513.248.8300

www.goldeneagleextrusions.com
info@goldeneagleextrusions.com

LFO-350PW

STANDARD THICKNESS - 3.5 MIL

LFO-350PW is a white, medium barrier, heat sealable and peelable lidding film. This film is designed to adhere to Polypropylene substrates with a light to medium seal.

Key Features

- Excellent moisture barrier
- Medium oxygen barrier
- Strong, durable film
- Superior machinability

PROPERTIES	UNIT	TESTING METHOD	TYPICAL VALUES
MECHANICAL			
Tensile Strength MD TD	lb/in ²	ASTM D882	11,800 11,800
Elongation MD TD	%	ASTM D882	100 100
PHYSICAL			
Yield	in ² /lb		7,900
COF Sealant side Heat resistant side	GRAMS	ASTM D1894	<.35 0.55
BARRIER			
MVTR	g/100 in ² /day	ASTM F1249 38°C, 100%RH	0.4
OTR	cc/100 in ² /day	ASTM D3985 23°C, 0%RH	6.0
THERMAL			
Vicant Softening Temperature	F	ASTM D1525	270°

Disclaimer: Nothing in this data sheet is to be taken as a warranty. Offered for your consideration only, the information provided herein represents our best knowledge and judgment. Golden Eagle Extrusions, Inc. assumes no liability whatsoever in connection with the use of this information.